



QUREACC CDMC

Copper Dimethyl dithiocarbamate

CAS No : 137-29-1
Molecular Formula : $C_6H_{12}CuN_2S_4$
Molecular weight : 303.96

SALES SPECIFICATIONS:

PARAMETER	UNIT	REQUIREMENT
Appearance	NA	Dark Brown Powder
Assay	%	99 Min.
Melting Point	°C	310 Min.
Loss On Drying (105°C)	%	1.0 Max.
Copper Content	%	19.0 - 21.0

APPLICATION

QUREACC CDMC used in SBR, IIR, EPDM ultra accelerator for high speed vulcanization not recommended for natural rubber. Generally used with thiazole modifier to control scorch rate.

PACKING AND STORAGE

Available in 10/25 Kg. Paper bag.
To be stored in a clean, cool & dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

HEAD OFFICE

Office No. 101 & 102,
Peninsula Heights,
C.D.Barfiwala Marg,
Juhu Lane,
Andheri (West),
Mumbai – 400058, India
TEL : 022 – 62510100
FAX : 022 – 62510199
E-Mail.: info@yashoindustries.com
Website : www.yashoindustries.com

FACTORY – UNIT II

Plot No. 1713
Phase III, G.I.D.C
Vapi - 396 195,
Gujarat, India
TEL. :- 0260 – 2420896 / 2423896

Rev.02 DT.05.05.2017