



QUREACC CDMC

Copper Dimethyl dithio Carbamate

CAS RN : 137-29-1

Molecular Weight : 467.47

SALES SPECIFICATION

Appearance	Dark Brown Powder
Assay	96 % Min.
Specific Gravity	1.75 g/cm ³
Melting Point	310 °C Min.
Loss on drying (105 ⁰ C)	1.0 % Max.
Copper Content	19 – 21%

APPLICATION

QUREACC CDMC used in SBR, IIR, EPDM ultra accelerator for high speed vulcanization not recommended for natural rubber Generally used with thiazole modifier to control scorch rate.

Dosage

SBR – Primary accelerator – 0.2 to 0.75 phr

Secondary accelerator 0.05 to 0.2 phr

IIR – Primary accelerator – 1 to 2 phr

PACKING AND STORAGE

Available in 10/25 Kg. Paper bag.

To be stored in a clean, cool & dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

OFFICE

31-H, LAXMI INDL.ESTATE,
NEW LINK ROAD, ANDHERI (W)
MUMBAI 400 053. INDIA
TEL: 91-22-66929152, 66929153,26310350
FAX: 91 - 22 - 66929154
E-Mail: info@yashoindustries.com

FACTORY

Plot No.1713, Phase III,
G.I.D.C., Vapi – 396 195
Dist.Bulsar,
GUJARAT, INDIA.
Tel: (0260) 2420896, 2423896
Fax.: (0260)2423996

Rev. DT.01.03.2013