



# QUREACC CDMC

## Copper Dimethyl dithiocarbamate

CAS No : 137-29-1  
Molecular Formula :  $C_6H_{12}CuN_2S_4$   
Molecular weight : 303.96

### SALES SPECIFICATIONS:

PARAMETER	UNIT	REQUIREMENT
Appearance	NA	Dark Brown Powder
Assay	%	99 Min.
Melting Point	°C	310 Min.
Loss On Drying (105°C)	%	1.0 Max.
Copper Content	%	19.0 - 21.0

### APPLICATION

QUREACC CDMC used in SBR, IIR, EPDM ultra accelerator for high speed vulcanization not recommended for natural rubber. Generally used with thiazole modifier to control scorch rate.

### PACKING AND STORAGE

Available in 10/25 Kg. Paper bag.  
To be stored in a clean, cool & dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

### YASHO INDUSTRIES PVT. LTD.

#### HEAD OFFICE

Office No. 101 & 102,  
Peninsula Heights,  
C.D.Barfiwala Marg,  
Juhu Lane,  
Andheri (West),  
Mumbai – 400058, India  
TEL : 022 – 62510100  
FAX : 022 – 62510199  
E-Mail.: [info@yashoindustries.com](mailto:info@yashoindustries.com)  
Website : [www.yashoindustries.com](http://www.yashoindustries.com)

#### FACTORY – UNIT II

Plot No. 1713  
Phase III, G.I.D.C  
Vapi - 396 195,  
Gujarat, India  
TEL. :- 0260 – 2420896 / 2423896

Rev.02 DT.05.05.2017