



QUREACC DOTG

Di-Ortho-tolylguanidine

CAS No : 97-39-2
Molecular Formula : C₁₅H₁₇N₃
Molecular weight : 239.32

SALES SPECIFICATIONS:

PARAMETER	UNIT	REQUIREMENT
Appearance	NA	White to Grey Powder
Assay (HPLC)	%	99 Min.
Melting Point	°C	171 Min.
Loss on Drying (105°C)	%	0.5 Max.
Ash Content	%	0.5 Max.

APPLICATION

QUREACC DOTG cause very slow onset & relatively slow rate of cure. QUREACC DOTG used on its own gives a stronger reversion, therefore the use of effective antioxidants is recommended.

It is used in combination with mercapto, sulphenamide, thiuram and dithiocarbamate accelerators, reciprocal activation and secondary acceleration can be achieved. Cross linking density and rate of cure are increased. Good mechanical properties and good ageing resistance are obtained. It has tendency to bloom in the vulcanization.

PACKING AND STORAGE

Available in 25 kg Paper Bags
To be stored in a clean cool place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

HEAD OFFICE

Office No. 101 & 102,
Peninsula Heights,
C.D.Barfiwala Marg,
Juhu Lane,
Andheri (West),
Mumbai – 400058, India
TEL : 022 – 62510100
FAX : 022 – 62510199
E-Mail.: info@yashoindustries.com
Website : www.yashoindustries.com

FACTORY – UNIT II

Plot No. 1713
Phase III, G.I.D.C
Vapi - 396 195,
Gujarat, India
TEL. :- 0260 – 2420896 / 2423896

Rev.02 DT.05.05.2017