



# QUREACC DPG

Diphenyl Guanidine

CAS RN : 102-06-7

Molecular Weight : 211

## TYPICAL SALES SPECIFICATION

Appearance	White to Light Pinkish Powder Low Dust
Assay (HPLC)	98 % Min.
Melting Point	145 °C Min.
Loss on drying (105°C)	0.50 % Max.
Ash Content	0.30 % Max.

## APPLICATION

QUREACC DPG gives very long scorch time and relatively slow full cure. It cause slight discoloration and cannot be used in light coloured articles, except as an activator. When QUREACC DPG is used on its own, the resistance of the vulcanizates to hot air and oxygen is poor. Aceleators of the mercapto types are strongly activates by QUREACC DPG.

## PACKING AND STORAGE

Available in 25 Kg. Paper Bags

To be stored in a clean cool place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

## YASHO INDUSTRIES PVT. LTD.

### OFFICE

31-H, LAXMI INDL. ESTATE,  
NEW LINK ROAD, ANDHERI (W)  
MUMBAI 400 053. INDIA  
TEL : 91-22-66929152, 66929153, 26310350  
FAX : 91 - 22 - 66929154  
E-Mail.: [info@yashoindustries.com](mailto:info@yashoindustries.com)  
Website: [www.yashoindustries.com](http://www.yashoindustries.com)

### FACTORY

PLOT NO.1713,  
PHASE III, G.I.D.C.,  
VAPI - 396 195.  
GUJARAT, INDIA.  
TEL. :-91 (260) 2420896 / 2423896  
FAX :-91 (260) 2423996

Rev. 02 DT.01.03.2013