



QUREACC DPG

Diphenyl Guanidine

CAS No : 102-06-7
Molecular Formula : $C_{13}H_{13}N_3$
Molecular weight : 211

SALES SPECIFICATIONS:

PARAMETER	UNIT	REQUIREMENT
Appearance	NA	White to Light Pinkish Powder Low Dust
Assay	%	98 Min.
Melting Point	°C	145 Min.
Loss on Drying (105°C)	%	0.5 Max.
Ash Content	%	0.3 Max.

APPLICATION

QUREACC DPG gives very long scorch time and relatively slow full cure. It cause slight discoloration and cannot be used in light coloured articles, except as an activator. When QUREACC DPG is used on its own, the resistance of the vulcanization to hot air and oxygen is poor. Accelerators of the mercapto types are strongly activated by QUREACC DPG.

PACKING AND STORAGE

Available in 25 kg Paper Bags
To be stored in a clean cool place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

HEAD OFFICE

Office No. 101 & 102,
Peninsula Heights,
C.D.Barfiwala Marg,
Juhu Lane,
Andheri (West),
Mumbai – 400058, India
TEL : 022 – 62510100
FAX : 022 – 62510199
E-Mail.: info@yashoindustries.com
Website : www.yashoindustries.com

FACTORY – UNIT II

Plot No. 1713
Phase III, G.I.D.C
Vapi - 396 195,
Gujarat, India
TEL. :- 0260 – 2420896 / 2423896

Rev.02 DT.05.05.2017