



QUREACC DPTU

Diphenyl Thiourea

CAS No : 102-08-9
Molecular Formula : $C_{13}H_{12}N_2S$
Molecular weight : 228.31

SALES SPECIFICATIONS:

PARAMETER	UNIT	REQUIREMENT
Appearance	NA	White to Grey Powder
Assay (HPLC)	%	98 Min.
Melting Point	°C	150 – 156
Loss On Drying (105°C)	%	0.5 Max.
Ash Content	%	0.3 Max.

APPLICATION

QUREACC DPTU causes very fast vulcanization of CR and is especially suitable as a secondary accelerators in self-curing CR compounds containing QUREACC ETU as a primary accelerator.

In EPDM it acts as an additional accelerator. In many cases it reduces the blooming tendency of other accelerators. In other diene rubbers, for example, in NR and SBR, it proves to be a strong activating agent and secondary accelerator, especially when sulphurless cures, E.V. or semi E.V. system are used.

PACKING AND STORAGE

Available in 25 Kg. Paper bag.
To be stored in a clean, cool & dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

HEAD OFFICE

Office No. 101 & 102,
Peninsula Heights,
C.D.Barfiwala Marg,
Juhu Lane,
Andheri (West),
Mumbai – 400058, India
TEL : 022 – 62510100
FAX : 022 – 62510199
E-Mail.: info@yashoindustries.com
Website : www.yashoindustries.com

FACTORY – UNIT II

Plot No. 1713
Phase III, G.I.D.C
Vapi - 396 195,
Gujarat, India
TEL. :- 0260 – 2420896 / 2423896

Rev.02 DT.05.05.2017