



QUREACC DPTU

Diphenyl Thiourea

CAS RN : 102-06-7

Molecular Weight : 211

TYPICAL SALES SPECIFICATION

Appearance	White Powder
Assay (HPLC)	98 % Min.
Melting Point	150 – 156 °C
Loss on drying (105 °C)	0.50 % Max.
Ash Content	0.30 % Max.

APPLICATION

QUREACC DPTU gives very long scorch time and relatively slow full cure. It cause slight discoloration and cannot be used in light coloured articles, except as an activator. When QUREACC DPTU is used on its own, the resistance of the vulcanizates to hot air and oxygen is poor. Aceleators of the mercapto types are strongly activates by QUREACC DPTU.

PACKING AND STORAGE

Available in 25 Kg. Paper Bags

To be stored in a clean cool place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

OFFICE

31-H, LAXMI INDL. ESTATE,
NEW LINK ROAD, ANDHERI (W)
MUMBAI 400 053. INDIA
TEL : 91-22-66929152, 66929153, 26310350
FAX : 91 - 22 - 66929154
E-Mail.: info@yashoindustries.com
Website: www.yashoindustries.com

FACTORY

PLOT NO.1713,
PHASE III, G.I.D.C.,
VAPI - 396 195.
GUJARAT, INDIA.
TEL. :-91 (260) 2420896 / 2423896
FAX :-91 (260) 2423996

Rev. 02 DT.01.03.2013