



QUREACC ETU

Ethylenethiourea

CAS RN : 96-45-7
Molecular Weight : 102.16

SALES SPECIFICATION

| | |
|-------------------------|----------------------------|
| Appearance | White or Light Buff Powder |
| Assay (HPLC) | 98 % Min. |
| Melting Point | 193 °C Min. |
| Loss on drying (105 °C) | 0.50 % Max. |
| Ash Content | 0.50 % Max. |

APPLICATION

Generally recommended for CR and Chlorobutyl compounds.
Suggest 0.5 – 1.0% dosage for improved safety and physical properties.

For better physical properties, recommended to be added after the compound has matured.

PACKING AND STORAGE

Available in 25 Kg Paper Bags
To be stored in a clean cool place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

OFFICE

31-H, LAXMI INDL. ESTATE,
NEW LINK ROAD, ANDHERI (W)
MUMBAI 400 053, INDIA
TEL : 91-22-66929152, 66929153, 26310350
FAX : 91 - 22 - 66929154
E-Mail.: info@yashoindustries.com
Website: www.yashoindustries.com

FACTORY

PLOT NO.1713,
PHASE III, G.I.D.C.,
VAPI - 396 195.
GUJARAT, INDIA.
TEL. :-91 (260) 2420896 / 2423896
FAX :-91 (260) 2423996

Rev. 02 DT.01.03.2013