



QUREACC MPTD

Dimethyl Diphenyl thiuram Disulfide

CAS No : 53880-86-7
Molecular Formula : $C_{16}H_{16}N_2S_4$
Molecular weight : 364.56

SALES SPECIFICATIONS:

PARAMETERS	UNIT	REQUIREMENT
Appearance	NA	Whitish Gray to Yellow Powder
Assay	%	98 Min.
Melting Point	°C	180 Min.
Loss on Drying (105°C)	%	0.5 Max.
Ash Content	%	0.3 Max.

APPLICATION

QUREACC MPTD is an ultra fast accelerator which is used alone or in combination with thiazoles and sulphenamides. MPTD is activated by basic accelerators such as DPG/DOTG and ETU. QUREACC MPTD gives excellent heat and reversion resistance and very good compression set in sulphurless curing. Tendency for blooming is lower than TMTD or TMTM. No discoloration of vulcanization.

General Purpose: Technical Goods, Tyre Tubes, Cables etc. requiring good heat resistance. White and light coloured rubber goods.

PACKING AND STORAGE

Available in 25 Kg. Paper Bags
To be stored in a clean, cool & dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

HEAD OFFICE

Office No. 101 & 102,
Peninsula Heights,
C.D.Barfiwala Marg,
Juhu Lane,
Andheri (West),
Mumbai – 400058, India
TEL : 022 – 62510100
FAX : 022 – 62510199
E-Mail.: info@yashoindustries.com
Website : www.yashoindustries.com

FACTORY – UNIT II

Plot No. 1713
Phase III, G.I.D.C
Vapi - 396 195,
Gujarat, India
TEL. :- 0260 – 2420896 / 2423896

Rev.02 DT.05.05.2017