

# **QUREACC TAC**

## **Triallyl Cyanurate**

CAS No : 101-37-1Molecular Formula :  $C_{12}H_{15}N_3O_3$ Molecular Weight : 249.27

## **SALES SPECIFICATIONS:**

PARAMETER	UNIT	REQUIREMENT
Appearance	NA	Slightly Yellowish Liquid
Active content	%	99 Min.
Melting Point	°C	26 - 28

### **APPLICATION**

QUREACC TAC is widely used as Co-agent for Peroxide curing of synthetic rubbers such as EPDM, CPE, EVA etc.

It improves heat resistance, mechanical properties and compression set of rubber products. QUREACC TAC in pure form is a yellow liquid at temperatures at around  $30^{\circ}$ C It solidifies to white solid at about  $25^{\circ}$ C.

## PACKING AND STORAGE

Available in 10/25 Kg.

To be stored in a clean, cool & dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

#### YASHO INDUSTRIES PVT. LTD.

#### HEAD OFFICE

Office No. 101 & 102, Peninsula Heights, C.D.Barfiwala Marg, Juhu Lane,

Andheri (West),

Mumbai – 400058, India TEL: 022 – 62510100 FAX: 022 – 62510199

E-Mail.: <a href="mailto:info@yashoindustries.com">info@yashoindustries.com</a> Website: <a href="mailto:www.yashoindustries.com">www.yashoindustries.com</a> FACTORY – UNIT II

Plot No. 1713 Phase III, G.I.D.C Vapi - 396 195, Gujarat, India

TEL.: - 0260 - 2420896 / 2423896

Rev.02 DT.05.05.2017