



QUREACC TBBS

Tert-butyl benzothiazole sulphenamide

CAS No. : 95-31-8
Molecular Formula : C₁₁H₁₄N₂S₂
Molecular Weight : 238.37

SALES SPECIFICATIONS:

PARAMETER	UNIT	REQUIREMENT
Appearance	NA	Off white to cream granules
Assay	%	99 Min.
Melting Point	°C	104 - 113
Loss on Drying (70°C)	%	0.5 Max.
Ash Content	%	0.5 Max.

APPLICATION

- Delayed action accelerator
- Provides good scorch safety in high reinforced tyre compounds, without sacrificing cure rate
- Vulcanisates have good physical, ageing properties and provides reversion resistance
- Approximately 10% less levels required than with CBS

PACKING AND STORAGE

Available in 25 Kg. Paper Bag
To be stored in a clean, cool & dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

HEAD OFFICE

Office No. 101 & 102,
Peninsula Heights,
C.D.Barfiwala Marg,
Juhu Lane,
Andheri (West),
Mumbai – 400058, India
TEL : 022 – 62510100
FAX : 022 – 62510199
E-Mail.: info@yashoindustries.com
Website : www.yashoindustries.com

FACTORY – UNIT II

Plot No. 1713
Phase III, G.I.D.C
Vapi - 396 195,
Gujarat, India
TEL. :- 0260 – 2420896 / 2423896

Rev.02 DT.05.05.2017