



QUREACC TBBS

Tert-Butyl Benzothiazole Sulphenamide

CAS RN : 95-31-8
Empirical Formula : C₁₁H₁₄S₂N₂
Molecular Weight : 238.37

SALES SPECIFICATION

Appearance	Off-White to Cream Granule
Assay	95 % Min.
Melting Point	104 – 113 °C
Loss on drying (70°C)	0.50 % Max.
Ash Content	0.50 % Max.

APPLICATION

- Delayed action accelerator.
- Provides good scorch safety in high reinforced tyre compounds, without sacrificing cure rate.
- Vulcanisates have good physical, ageing properties and provides reversion resistance.
- Approximately 10% less levels required than with CBS

PACKING AND STORAGE

Available in 25 Kgs Bag
To be stored in a clean, cool & dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

OFFICE

31-H, LAXMI INDLESTATE,
NEW LINK ROAD, ANDHERI (W)
MUMBAI 400 053. INDIA
TEL : 91-22-66929152, 66929153,26310350
FAX : 91 - 22 - 66929154
E-Mail.: info@yashoindustries.com
Website: www.yashoindustries.com

FACTORY

PLOT NO.1713,
PHASE III, G.I.D.C.,
VAPI - 396 195.
GUJARAT, INDIA.
TEL. :-91 (260) 2420896 / 2423896
FAX :-91 (260) 2423996

Rev. 02 DT.01.03.2011