



# QUREACC TDEC

## Tellurium Diethyldithiocarbamate

CAS No. : 20941-65-5  
Molecular Formula :  $C_{20}H_{40}N_4S_8Te$   
Molecular Weight : 720.65

### SALES SPECIFICATIONS:

PARAMETER	UNIT	REQUIREMENT
Appearance	NA	Orange to red coloured powder
Assay	%	96 Min.
Tellurium content	%	16 – 18
Melting Point	°C	108 – 118
Specific Gravity	g/cm <sup>3</sup>	1.5
Solubility	NA	Soluble in Chloroform, Toluene, etc. Insoluble in water

### APPLICATION

QUREACC TDEC is widely used in the manufacturer of extruded EPDM rubber sponge for Automobile doors where partial rapid curing is desired before blowing of rubber. Typical usage level in EPDM sponge is 0.3 parts. Higher levels give good compression set but blooming can occur.

### PACKING AND STORAGE

Available in 10/25 Kg. Drum.  
To be stored in a clean, cool & dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

### YASHO INDUSTRIES PVT. LTD.

#### HEAD OFFICE

Office No. 101 & 102,  
Peninsula Heights,  
C.D.Barfiwala Marg,  
Juhu Lane,  
Andheri (West),  
Mumbai – 400058, India  
TEL : 022 – 62510100  
FAX : 022 – 62510199  
E-Mail.: [info@yashoindustries.com](mailto:info@yashoindustries.com)  
Website : [www.yashoindustries.com](http://www.yashoindustries.com)

#### FACTORY – UNIT II

Plot No. 1713  
Phase III, G.I.D.C  
Vapi - 396 195,  
Gujarat, India  
TEL. :- 0260 – 2420896 / 2423896