



QUREACC TMTM

Tetra Methyl Thiurammonosulfide

CAS No. : 97-74-5
Molecular Formula : $C_6H_{12}N_2S_3$
Molecular Weight : 208.36

SALES SPECIFICATIONS:

PARAMETER	UNIT	REQUIREMENT
Appearance	NA	Yellow Powder
Assay	%	99 Min.
Melting Point	°C	104 – 107 Min.
Loss on Drying (70°C)	%	0.5 Max.
Ash Content	%	0.5 Max.

APPLICATION

QUREACC TMTM cause very rapid and scorch safe vulcanization of natural & synthetics rubbers. Recommended in natural, SBR, butyl, nitrile and neoprene rubbers. It is commonly used as sulphur donor to get excellent after ageing properties.

PACKING AND STORAGE

Available in 25 Kg. Paper Bag
To be stored in a clean, cool & dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

HEAD OFFICE

Office No. 101 & 102,
Peninsula Heights,
C.D.Barfiwala Marg,
Juhu Lane,
Andheri (West),
Mumbai – 400058, India
TEL : 022 – 62510100
FAX : 022 – 62510199
E-Mail.: info@yashoindustries.com
Website : www.yashoindustries.com

FACTORY – UNIT II

Plot No. 1713
Phase III, G.I.D.C
Vapi - 396 195,
Gujarat, India
TEL. :- 0260 – 2420896 / 2423896

Rev.02 DT.05.05.2017