



QUREACC TMTM

Tetramethylthiuram Monosulfide

CAS RN : 97-74-5
Molecular Weight : 208

SALES SPECIFICATION

Appearance	Yellow Powder
Assay	96 % Min.
Melting Point	104 –107 °C
Loss on drying (70°C)	0.50 % Max.
Ash Content	0.50 % Max.

APPLICATION

TMTM cause very rapid and scorch safe vulcanization of natural & synthetics rubbers. Recommended in natural, SBR, butyl, nitrile and neoprene rubbers.

It is commonly used as sulphur donor to get excellent after ageing properties.

PACKING AND STORAGE

Available in 25 Kg. Paper Bags
To be stored in a clean cool place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

OFFICE

31-H, LAXMI INDLESTATE,
NEW LINK ROAD, ANDHERI (W)
MUMBAI 400 053. INDIA
TEL : 91-22-66929152, 66929153,26310350
FAX : 91 - 22 - 66929154
E-Mail.: info@yashoindustries.com
Website: www.yashoindustries.com

FACTORY

PLOT NO.1713,
PHASE III, G.I.D.C.,
VAPI - 396 195.
GUJARAT, INDIA.
TEL. :-91 (260) 2420896 / 2423896
FAX :-91 (260) 2423996

Rev. 02 DT.01.03.2013