



# QUREACC<sup>®</sup>ZIX

## Zinc Isopropylxanthate

CAS No. : 1000-90-4  
Molecular Formula : C<sub>8</sub>H<sub>14</sub>O<sub>2</sub>S<sub>2</sub>Zn  
Molecular Weight : 336

### **SALES SPECIFICATIONS:**

PARAMETER	UNIT	REQUIREMENT
Appearance	NA	White to Light Yellow powder
Melting Point	°C	140.0 Min.
Loss on Drying (105°C)	%	1.0 Max.
Zinc Content	%	18.0 – 21.0

### **APPLICATION**

QUREACC<sup>®</sup>ZIX is used as a secondary accelerator for natural and synthetic rubbers. This accelerator is recommended for very fast cure and have applications in shoe, adhesives and other moulded products. Curing at low temperatures with this accelerator is preferred. Also used as an accelerator in NR & synthetic latex to prevent copper discoloration.

Recommended dosage is from 0.5 – 1.5 phr.

### **PACKING AND STORAGE**

Available in 10/25 Kg. Paper Bag.  
To be stored in a clean, cool & dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

### **YASHO INDUSTRIES LIMITED**

#### **REGISTERED OFFICE**

Office No. 101/102, Peninsula Heights,  
C.D.Barfiwala Marg, Juhu lane,  
Andheri (West), Mumbai – 400058, India  
TEL : +91 22 62510100  
FAX : +91 22 62510199  
E-Mail.: [info@yashoindustries.com](mailto:info@yashoindustries.com)  
Website : [www.yashoindustries.com](http://www.yashoindustries.com)

#### **FACTORY – UNIT II**

Plot No. 1713,  
Phase III, G.I.D.C.,  
Vapi - 396 195,  
Gujarat, India  
TEL.: +91 260 2420896 / 2423896

QUREACC is a registered trademark of YASHO INDUSTRIES LIMITED and/or its respective wholly owned subsidiaries

Rev.02 DT.01.03.2019