



QURECURR PDM

N,N'-1,3-Phenylenedimaleimide

CAS No. : 3006-93-7

Molecular Formula : $C_{14}H_8N_2O_4$

Molecular weight : 268.23

SALES SPECIFICATIONS:

| PARAMETER | UNIT | REQUIREMENT |
|---------------|------|----------------------------------|
| Appearance | NA | Yellow to greenish yellow powder |
| Melting Point | °C | 198 Min. |
| Ash Content | % | 0.5 Max. |
| Heat Loss | % | 0.5 Max. |

APPLICATION

QURECURR PDM is used as co-agent in Peroxide curing where it improves crosslink density, enabling lower levels of peroxide usage, improves adhesion to textile cords and to metals. It is also used in peroxide free formulations such as in NR curing sulphur, where it improves reversion resistance, heat and ageing resistance and adhesion strength to textile cords and steel wires. It is recommended in all specialty rubbers like CR, CSM, NBR, Acrylic Rubber, EPDM and it blends with PP plastic.

PACKING AND STORAGE

Available in 25 Kgs. Paper Bags

To be stored in a clean, cool & dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

HEAD OFFICE

Office No. 101 & 102,
Peninsula Heights,
C.D.Barfiwala Marg,
Juhu Lane,
Andheri (West),
Mumbai – 400058, India
TEL : 022 – 62510100
FAX : 022 – 62510199
E-Mail.: info@yashoindustries.com
Website : www.yashoindustries.com

FACTORY – UNIT II

Plot No. 1713
Phase III, G.I.D.C
Vapi - 396 195,
Gujarat, India
TEL. :- 0260 – 2420896 / 2423896

Rev.02 DT.22.07.2017