



YAPOX 2275

2,5-Di-tertiary amyl hydroquinone

CAS No. : 79-74-3
Molecular Formula : C₁₄H₂₀O₂
Molecular Weight : 250.38

SALES SPECIFICATIONS:

PARAMETER	UNIT	REQUIREMENT
Appearance	NA	White to Off white powder
Assay	%	95 Min.
Odour	NA	Characteristic
Melting Point	°C	177 – 184
Volatiles	%	0.5 Max.
Ash Content	%	0.1 Max.

APPLICATION

YAPOX 2275 is used as Primary antioxidant / stabilizer for synthetic rubbers acrylonitrile (NBR) especially effective against sunlight. Good drying / tack retention properties.

PACKING AND STORAGE

Available in 25 Kg. Fibre Drum.
To be stored in a clean cool place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

HEAD OFFICE

Office No. 101 & 102,
Peninsula Heights,
C.D.Barfiwala Marg,
Juhu Lane,
Andheri (West),
Mumbai – 400058, India
TEL : 022 – 62510100
FAX : 022 – 62510199
E-Mail.: info@yashoindustries.com
Website : www.yashoindustries.com

FACTORY – UNIT I

Plot No. 2514/2515,
Phase IV, G.I.D.C.,
Vapi - 396 195,
Gujarat, India
TEL. :- 0260 - 2432421 / 2426894 / 2420447

Rev.02 DT.05.05.2017