



YAPOX-CL 30 / 10

**4-Hydroxyethoxy-1-hydroxyethylbenzendiether
Hydroquinone Bis(2-Hydroxyethyl) ether (HQEE)**

CAS RN : 104-38-1

SALES SPECIFICATION

Appearance	Grayish white powder / Pallets
Melting Point	104°C Min
Moisture Content	0.1 % Max.
Solidification time	100 + 20 Sec
Hydroxyl number	560 ± 20 mg KOH/gm

APPLICATION

Crosslinking agent / as a chain extender for polyurethanes (PU)

PACKING AND STORAGE

Available in 120 Kg. Drum

To be stored in a closed container in a clean cool place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

OFFICE

31-H, LAXMI INDL.ESTATE,
NEW LINK ROAD, ANDHERI (W)
MUMBAI 400 053. INDIA
TEL: 91-22-66929152, 66929153,26310350
FAX: 91 - 22 - 66929154
E-Mail: info@yashoindustries.com
Website: www.yashoindustries.com

FACTORY

PLOT NO.2514-2515,
PHASE IV, G.I.D.C.,
VAPI - 396 195.
GUJARAT, INDIA.
TEL.: - (0260) 2432421 / 2426894
FAX: - (0260) 2410409

Rev. 02 DT.01.03.2013