



# QUREACC<sup>®</sup>BiDD

## Bismuth Dimethyl Dithiocarbamate

CAS No. : 21260-46-8  
Molecular Formula : C<sub>9</sub>H<sub>18</sub>BiN<sub>3</sub>S<sub>6</sub>  
Molecular weight : 570

### **SALES SPECIFICATIONS:**

PARAMETER	UNIT	REQUIREMENT
Appearance	NA	Coarse Bright Yellow Powder
Loss on Drying (40°C)	%	0.50 Max.
Bismuth Content	%	35.0 - 38.0

### **APPLICATION**

**QUREACC<sup>®</sup>BiDD** is accelerator used along with MBTS and Sulphur for High Temperature (160°C), High Speed Vulcanization of NR and SBR Rubbers. It is Primarily used in Wire and Cables Vulcanization of NR, SBR at High Temperature for Short Time.

### **PACKING AND STORAGE**

Available in 25 kgs. Drum  
To be stored in a clean, cool and dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

### **YASHO INDUSTRIES LIMITED**

#### **REGISTERED OFFICE**

Office No. 101/102, Peninsula Heights,  
C.D.Barfiwala Marg, Juhu lane,  
Andheri (West), Mumbai – 400058, India  
TEL : +91 22 62510100  
FAX : +91 22 62510199  
E-Mail.: [info@yashoindustries.com](mailto:info@yashoindustries.com)  
Website : [www.yashoindustries.com](http://www.yashoindustries.com)

#### **FACTORY – UNIT II**

Plot No. 1713,  
Phase III, G.I.D.C.,  
Vapi - 396 195,  
Gujarat, India  
TEL.: +91 260 2420896 / 2423896

QUREACC is a registered trademark of YASHO INDUSTRIES LIMITED and/or its respective wholly owned subsidiaries

Rev.02 DT.01.03.2019