



QUREACC TBTD

Tetra Butyl Thiuram Disulfide

CAS No. : 1634-02-2
Molecular Formula : $C_{18}H_{36}N_2S_4$
Molecular Weight : 408.74

SALES SPECIFICATIONS:

PARAMETER	UNIT	REQUIREMENT
Appearance	NA	Dark Amber Liquid
Assay	%	98 Min.
Specific Gravity	gm/ml	1.04 – 1.08
Heat Loss at 60 – 65°C	%	3.0 Max.
Ash Content	%	0.5 Max.

APPLICATION

QUREACC TBTD is used as sulfur donor accelerator for soluble cure systems in natural and polyisoprene rubbers. It is used in conjunction with amly ledate in EPDM.

PACKING AND STORAGE

Available in 30/200 Kg. Drum
To be stored in a clean, cool & dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES PVT. LTD.

HEAD OFFICE

Office No. 101 & 102,
Peninsula Heights,
C.D.Barfiwala Marg,
Juhu Lane,
Andheri (West),
Mumbai – 400058, India
TEL : 022 – 62510100
FAX : 022 – 62510199
E-Mail.: info@yashoindustries.com
Website : www.yashoindustries.com

FACTORY – UNIT II

Plot No. 1713
Phase III, G.I.D.C
Vapi - 396 195,
Gujarat, India
TEL. :- 0260 – 2420896 / 2423896

Rev.02 DT.05.05.2017