



QUREACC[®]TDEC

Tellurium Diethyldithiocarbamate

CAS No. : 20941-65-5
Molecular Formula : C₂₀H₄₀N₄S₈Te
Molecular Weight : 721

SALES SPECIFICATIONS:

PARAMETER	UNIT	REQUIREMENT
Appearance	NA	Orange to yellow coloured powder
Assay	%	96.0 Min.
Tellurium content	%	16.5 – 19.0
Melting Point	°C	112.0 – 122.0
Loss on Drying	%	0.50 Max.
Solubility	NA	Soluble in Chloroform, Toluene, etc. Insoluble in water

APPLICATION

QUREACC[®]TDEC is widely used in the manufacturer of extruded EPDM rubber sponge for Automobile doors where partial rapid curing is desired before blowing of rubber. Typical usage level in EPDM sponge is 0.3 parts. Higher levels give good compression set but blooming can occur.

PACKING AND STORAGE

Available in 10/25 Kgs. Drum.
To be stored in a clean, cool & dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

YASHO INDUSTRIES LIMITED

REGISTERED OFFICE

Office No. 101/102, Peninsula Heights,
C.D.Barfiwala Marg, Juhu lane,
Andheri (West), Mumbai – 400058, India
TEL : +91 22 62510100
FAX : +91 22 62510199
E-Mail.: info@yashoindustries.com
Website : www.yashoindustries.com

FACTORY – UNIT II

Plot No. 1713,
Phase III, G.I.D.C.,
Vapi - 396 195,
Gujarat, India
TEL.: +91 260 2420896 / 2423896

QUREACC is a registered trademark of YASHO INDUSTRIES LIMITED and/or its respective wholly owned subsidiaries

Rev.02 DT.01.03.2019