



# QUREACC<sup>®</sup>TMTM

## Tetra Methyl Thiuram monosulfide

CAS No. : 97-74-5  
Molecular Formula : C<sub>6</sub>H<sub>12</sub>N<sub>2</sub>S<sub>3</sub>  
Molecular Weight : 208

### **SALES SPECIFICATIONS:**

PARAMETER	UNIT	REQUIREMENT
Appearance	NA	Yellow Powder
Assay	%	96.0 Min.
Melting Point	°C	104.0 – 107.0
Loss on Drying (70°C)	%	0.50 Max.
Ash Content	%	0.50 Max.

### **APPLICATION**

QUREACC<sup>®</sup>TMTM cause very rapid and scorch safe vulcanization of natural & synthetics rubbers. Recommended in natural, SBR, butyl, nitrile and neoprene rubbers. It is commonly used as sulphur donor to get excellent after ageing properties.

### **PACKING AND STORAGE**

Available in 25 Kgs. Paper Bag  
To be stored in a clean, cool & dry place.

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

### **YASHO INDUSTRIES LIMITED**

#### **REGISTERED OFFICE**

Office No. 101/102, Peninsula Heights,  
C.D.Barfiwala Marg, Juhu lane,  
Andheri (West), Mumbai – 400058, India  
TEL : +91 22 62510100  
FAX : +91 22 62510199  
E-Mail.: [info@yashoindustries.com](mailto:info@yashoindustries.com)  
Website : [www.yashoindustries.com](http://www.yashoindustries.com)

#### **FACTORY – UNIT II**

Plot No. 1713,  
Phase III, G.I.D.C.,  
Vapi - 396 195,  
Gujarat, India  
TEL.: +91 260 2420896 / 2423896

QUREACC is a registered trademark of YASHO INDUSTRIES LIMITED and/or its respective wholly owned subsidiaries

Rev.02 DT.01.03.2019